

# **Epoxycote SB** Solvent Based Epoxy Coating

# DESCRIPTION

Epoxycote SB is a solvent containing pigmented two component system based on liquid epoxy resin with a special amine hardener.

## USE

Epoxycote SB is a coating system for cement based surfaces such as concrete, plaster, asbestos cement and also for iron and steel. The main fields of application are floor and wall surfaces, which are subjected to normal mechanical loads and aggressive chemicals. Typical use includes, storage tanks and silos in chemical industry, food industry, drinking water storage tanks, swimming pools, sewage works, septic tanks, sewage pipe lines etc.,

## **ADVANTAGES**

Very hard and abrasion resistant

Weather and water proof,

Resistant to waste and sea water.

Suitable for organic and inorganic acids, Dyes, and mineral oils

Coated surface can be steam cleaned.

Impermeable to carbon-di-oxide, thus protects concrete against carbonization.

## PROPERTIES

Any desired colour
1
1.25 - 1.35
10
7
12 - 16
Min. 2
Brush / Roller
90 – 100 microns
Matt - Semi gloss

# **APPLICATION INSTRUCTIONS**

## Surface preparation:

Concrete surfaces should be free from laitance and dust by sandblasting. In case sand blasting is not possible, thorough abrading with a hard wire brush can be used, though it is not as efficient. Otherwise, acid etching using 1 part of Hydrochloric acid with 2 parts of water can be carried out. The solution should be brush applied over the surface liberally and left in contact for 15 minutes. Then it is washed off with plenty of water followed by thorough drying with hot water.



The pre-requisites for good adhesion of the coating are cleanliness, roughness and dryness of the surface. Unless these are ensured by proper surface preparation, a successful performance can not be guaranteed.

The degree of dampness of the surface must be less than 4%.

Iron and steel surfaces must be free from rust, scale, dust, grease and other impurities which can prevent adhesion. The best pre treatment is sand blasting to Sa 21/2. Bostik ZNP primer should be applied immediately after the removal of rust and other impurities.

#### APPLICATION Primer application:

One brush coat of the following system is recommended as a primer, on the already treated surface :

Primer E2 Base	0.6 part by weight
Primer E2 Hardener	0.4 parts by weight

Both the components are individually mixed thoroughly for homogeneity and then mixed together in the above recommended ratio and applied using the conventional brush. The primer should be allowed to be just tack-free prior to the application of coating

## **Coating application:**

Epoxycote SB Component A (base) should be thoroughly stirred before adding component B (hardener).Pour component B into component A and mix for 2 minutes with slow speed stirrer with suitable mixing paddle to get a consistent coating material. The coating is applied on the primer applied area evenly and a second coat is applied at right angles so that the entire area is fully covered, after the recommended interval of time.

#### Application on steel surface:

**<u>Primer</u>**: After proper surface preparation, like sand blasting, the surface is protected using Bostik ZNP , an epoxy zinc phosphate primer.

**Top coating**: Next day, two coats of Epoxycote SB is applied one after the other coat leaving the recommended time gap between coats, as described earlier.

#### Note:

1.Normally 2 - 3 top coats are recommended for protective treatment. The first top coat is applied over the primer coat and is left to dry. Next day, second day, next coat is applied, and if required third coat is done on the third day.

2. If longer intervals occur between individual coating or in case coating is to be removed, the old surface should be thoroughly roughened and cleaned.



3. Since this product contained solvents, it is essential that when working in closed areas like inside containers or silos, good ventilation must be provided.

4. Please check with us for suitability of the product against individual chemicals.

### CLEANING

Immediately after application of Epoxycote SB, clean the tools, equipment and the mixing container using solvents like Bostik Thinner E otherwise, removal of dried / hardened epoxy mortar is difficult.

#### COVERAGE

Primer – Primer E 2 : 5-6 Sq.mtr./kg Coating – Epoxycote SB: 6 sq.m/kg/coat 2 coats recommended to get 100 micron DFT Coverage may vary based on nature of substrate

#### PACKING

Epoxycote SB 5kg

#### **STORAGE & SHELF LIFE:**

Bostik Epoxycote SB Component A, and Component B as supplied shall be stored in a cool and dry place away from sunlight, moisture and high humidity and have a shelf life of 12 Months in the original packing.

#### **HEALTH & SAFETY:**

Epoxycote SB contains organic resins, hardener, solvents and other filler materials which may cause sensitization by skin contact. Avoid contact with skin and eyes and inhalation of vapour. In case of contact, wash liberally with water and seek medical advice, if required. Wear suitable protective clothing, gloves and goggles while handling.etc.,

#### WARRANTY

Whilst Bostik India P Ltd., strives to ensure that any advice, information or recommendation given are appropriate and correct, it cannot accept any liability directly or indirectly arising out of the products, since the method and place of application of the products are beyond its control. Its guarantee is therefore limited to the quality of materials delivered.

# **Our Authorized Distributors**



Landline : 080-28611303 / 28601393 Phone : +919538101456 / 9538501236 No 475-F2, Sourabha, Jawaharlal Nehru Road, BEML 3rd Stage, Opp Sub Register Office, RR Nagar, Bangalore, Karnataka, India – 560098

Mail: info@durgamba.co.in Web: www.durgamba.co.in