

Technical Data Sheet

BOSTIK LVEP

Low Viscous Epoxy Injection Resin Grout

DESCRIPTION

Epoxy Injection Grout consists of solvent free epoxy resin with low viscous liquid hardener. Epoxy injection grout may be placed by free flow under gravity or may be injected using suitable hand or mechanical pump. Grouting of a gap dimensions 0.1mm to10mm may be easily achieved

USES

Crack injection application
Filling and bonding of cracked concrete
Structural support where thin section grouting is required
Structural support where dynamic load resistance is required
Bonding of lifted floor toppings

FEATURES AND BENEFITS

Low viscosity and rapid strength gaining High mechanical strength Non shrink Good Chemical resistant

Properties

Pot life @ 25 degree C. : 30 minutes

Mixed viscosity : 200 cps

Density : 1.05-1.10

Compressive strength : 80 N/sq.mm

Flexural strength : 35 N/sq.mm

APPLICATION PROCEDURE

Surface Preparation

Ensure that grouting surfaces are free from dust and oil contamination Small gaps may be blown out by using clean dry compressed air Steel should be free of rust and flaking mill scale All work surfaces must be dry

MIXING

Add entire content hardener into base Mix thoroughly for 2 minutes with slow speed stirrer until to get homogeneous

PLACING

Pouring Under Gravity

For supporting structures, where epoxy injection grout is being poured under gravity, the



use of a grout tight shutter is essential .This may be constructed from timber and sealed using fast set mortar. Apply a mould releasing agent to the form work surfaces which will affect release after the grout has hardened .

CRACK INJECTION

Drill and fix suitable injection tubes at approximately 300mm centers along the crack line using fast set mortar for fixing the tubes and facing up the crack. Use low pressure pump to inject mixed grout starting at the lowest point of the crack and work upwards to the highest point sealing off each injection point in turn

Allow grout to cure for at least 24 hours .Cut off external parts of injection tubes and tools and equipment should be cleaned with solvent prior to grout setting

PACKAGING

Bostik LVEP is supplied in 1 and 4 kg

STORAGE & SHELF LIFE

Bostik LVEP as supplied shall be stored in a cool and dry place away from sunlight, moisture and high humidity and have a shelf life of 12 months in the original packing.

HEALTH &SAFETY

Bostik LVEP contains organic resins and hardeners which may cause sensitization by skin contact. Avoid contact with skin and eyes and inhalation of vapour. In case of contact, wash liberally with water and seek medical advice, if required. Wear suitable protective clothing, gloves and goggles while handling.

FIRE

Bostik LV EP is inflammable. No naked flame should be allowed near the site. Do not smoke during use.

WARRANTY

Whilst Bostik India (P) Ltd., strives to ensure that any advice, information or recommendation given are appropriate and correct, it cannot accept any liability directly or indirectly arising out of the products, since the method and place of application of the products are beyond its control. Its guarantee is therefore limited to the quality of materials delivered.



Our Authorized Distributors



No 475-F2, Sourabha, Jawaharlal Nehru Road, BEML 3rd Stage, Opp Sub Register Office, RR Nagar, Bangalore, Karnataka, India – 560098

Landline: 080-28611303 / 28601393 Phone: +919538101456 / 9538501236

Mail: info@durgamba.co.in Web: www.durgamba.co.in